

LA-2231

C-3

CIC-14 REPORT COLLECTION  
REPRODUCTION  
COPY

LOS ALAMOS SCIENTIFIC LABORATORY  
OF THE UNIVERSITY OF CALIFORNIA ○ LOS ALAMOS NEW MEXICO

---

THE PREPARATION OF PLUTONIUM ALLOYS  
IN THE REDUCTION PROCESS



## LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission to the extent that such employee or contractor prepares, handles or distributes, or provides access to, any information pursuant to his employment or contract with the Commission.

Printed in USA. Price 50 cents. Available from the

Office of Technical Services  
U. S. Department of Commerce  
Washington 25, D. C.

LA-2231  
METALLURGY AND CERAMICS  
TID-4500, 13th Ed., Rev.

**LOS ALAMOS SCIENTIFIC LABORATORY**  
**OF THE UNIVERSITY OF CALIFORNIA LOS ALAMOS NEW MEXICO**

REPORT WRITTEN: December 1957

REPORT DISTRIBUTED: October 10, 1958

THE PREPARATION OF PLUTONIUM ALLOYS  
IN THE REDUCTION PROCESS

Work done by:

A. N. Morgan, Jr.  
C. A. Emery  
C. A. Rendell

Report written by:

A. N. Morgan, Jr.

This report expresses the opinions of the author or authors and does not necessarily reflect the opinions or views of the Los Alamos Scientific Laboratory.

Contract W-7405-ENG. 36 with the U. S. Atomic Energy Commission

LOS ALAMOS NATIONAL LABORATORY

3 9338 00359 4685

#### ABSTRACT

Homogeneous binary alloys of plutonium with aluminum, iron, cobalt, nickel, copper and uranium have been prepared in the reduction process. The method is not applicable for plutonium-zirconium or plutonium-cerium alloys.

#### ACKNOWLEDGEMENTS

The author wishes to express his gratitude to R. D. Baker for his many helpful suggestions and to Group CMB-1 for performing the analyses.

## INTRODUCTION

Plutonium metal of high purity and yield is prepared by the calcium reduction of plutonium tetrafluoride using iodine as a booster.<sup>(1)</sup> Alloys of uranium with molybdenum<sup>(2)</sup> and niobium<sup>(3)</sup> have been prepared using the equivalent process with uranium tetrafluoride. More recently, the preparation of plutonium-aluminum alloys by aluminum-cryolite reduction process<sup>(4)</sup> and by the aluminum reduction of plutonium trifluoride and of aluminum dioxide<sup>(5)</sup> have been reported.

The preparation of alloys of plutonium with aluminum, iron, cobalt, nickel, copper, zirconium, uranium and cerium in the plutonium tetrafluoride process is reported below.

## PROCEDURE

In the metal reduction process plutonium tetrafluoride is intimately mixed with calcium metal and iodine. Iodine is used in a 1 to 10 molar ratio with plutonium. Calcium (-10 +40 mesh U. S. Standard sieve size) is added in an amount sufficient for both the plutonium tetrafluoride and iodine reaction plus a 25 percent excess. The mixture is poured into a magnesia crucible located inside a steel pressure chamber. The annular space between the ceramic crucible and the pressure chamber is tightly packed with magnesia sand to protect the crucible against thermal shock. The pressure chamber is sealed, evacuated and made inert with argon. The assembly is then placed inside an induction coil and the charge heated by induction heating. The plutonium tetrafluoride is reduced to elemental plutonium.

The methods used to introduce the alloying element into the plutonium tetrafluoride-calcium-iodine charge are by the direct addition of the element, either as a fluoride compound or as metallic powder or chips, into the calcium and iodine before mixing with the plutonium tetrafluoride, and by the loading of metallic powder or chips into the ceramic crucible before the premixed reduction charge is introduced.

#### PLUTONIUM-ALUMINUM ALLOY

Plutonium-aluminum alloys varying in aluminum content from 0.27 to 0.97 weight percent (w/o) have been made by adding 8-mesh aluminum pellets to the plutonium tetrafluoride prior to mixing. On a 350-g. scale the reduction yields have been greater than (>) 98.5 w/o and the aluminum yield has been within 0.03 w/o of the added concentration.

#### PLUTONIUM-IRON ALLOY

Plutonium-iron alloys ranging in iron content from 2.28 to 2.55 w/o have been produced in kilogram quantities. The most convenient method for the production of this alloy is by the direct addition of coarse iron powder to the plutonium tetrafluoride. Reduction yields of >99 w/o and iron concentrations within 0.01 w/o of the added amount have been obtained in this system.

#### PLUTONIUM-COBALT ALLOY

Cobalt metal turnings added to the ceramic crucible are used to produce 3.25 w/o cobalt-plutonium alloys. On a 350-g. scale, cobalt concentration within 0.16 w/o of the added amount and reduction yields of >99% have been achieved.

#### PLUTONIUM-NICKEL ALLOY

Kilogram quantities of plutonium-nickel alloys have been made. Similar to the cobalt alloy, nickel metal turnings are added to the ceramic crucible to produce a 3.39 w/o nickel-plutonium alloy on a 350-g. scale. Reduction yields of >98 w/o and a nickel concentration within 0.11 w/o of the added amount are readily produced.

#### PLUTONIUM-COPPER ALLOY

Plutonium-copper alloys containing 2.5 w/o copper have been produced on a 160-g. scale by adding 8-mesh copper pellets to the plutonium tetrafluoride. Copper concentration within 0.28 w/o of the added amount and 99 w/o reduction yields have been achieved.

#### PLUTONIUM-URANIUM ALLOY

Both plutonium-rich (65 w/o) alloys of uranium and uranium-rich (85 w/o) alloys of plutonium have been prepared on a 160-g. scale. These alloys are prepared by mixing the tetrafluoride compound of each element with calcium and iodine. Metal yields of >97 w/o have been obtained. In the uranium-rich alloy the plutonium concentration was exact, whereas in the plutonium-rich alloy the plutonium concentration was 2.4 w/o high.

#### PLUTONIUM-ZIRCONIUM ALLOY

Plutonium-zirconium alloys have been produced by adding zirconium metal to the magnesia crucible and by adding zirconium tetrafluoride to the plutonium tetrafluoride, calcium and iodine. On a 200-g. scale, reduction yields of >97 w/o were achieved. Chemical analysis for zirconium on multiple samples of the buttons showed concentrations from 0.53 to 0.78 w/o zirconium as compared to 0.75 w/o added.

### PLUTONIUM-CERIUM ALLOYS

A cerium-rich alloy (62 w/o) of plutonium has been made on a 360-g. scale by mixing cerium tetrafluoride with plutonium tetrafluoride, calcium and iodine. The button produced was well formed but porous. A cerium yield of 53.1 w/o and a reduction yield of >79 w/o was obtained.

### REFERENCES

1. Johnson, K. W. R., "The Preparation of High Purity Plutonium Metal," LA-1680, May, 1954.
2. Hayward, B. R., "Preparation of Uranium-Molybdenum Alloys by Bomb Reduction," LA-1405, Feb., 1952.
3. Hayward, B. R., "Preparation of Uranium-Columbium Alloys by Bomb Reduction," LA-1407, Feb., 1952.
4. Lyon, W. L., "Application of the Aluminum-Cryolite Reduction Process to the Plutonium Recycle Program," Hanford Works Report HW-52461, Sept. 17, 1957.
5. Runnals, C. J. C., and Wauchope, K. L., "The Preparation and Sheathing of Plutonium-Aluminum Fuel Alloys for the N. R. X. Reactor," Chalk River Report AECL-514, Nov., 1957.