

A major purpose of the Technical Information Center is to provide the broadest dissemination possible of information contained in DOE's Research and Development Reports to business, industry, the academic community, and federal, state and local governments.

Although a small portion of this report is not reproducible, it is being made available to expedite the availability of information on the research discussed herein.

1

Received by OSTI 14

APR 07 1986

Los Alamos National Laboratory is operated by the University of California for the United States Department of Energy under contract W-7405-ENG-36

LA-UR--86-1007

DE86 008758

TITLE ELECTRON MICROSCOPY OF ALPHA-PLUTONIUM

AUTHOR(S) Karl P. Staudhammer, MST-7
Kaye A. Johnson, MST-13
Michael F. Stevens, MST-5
Walter J. Medina, MST-13

SUBMITTED TO 44th Annual Meeting of the Electron Microcopy Society
of America, Albuquerque, NM, August 10-15, 1986

DISCLAIMER

MASTER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

By acceptance of this article the publisher recognizes that the U.S. Government retains a nonexclusive, royalty free license to publish or reproduce the published form of this contribution or to allow others to do so for U.S. Government purposes.

The Los Alamos National Laboratory requests that the publisher identify this article as work performed under the auspices of the U.S. Department of Energy.

Los Alamos Los Alamos National Laboratory
Los Alamos, New Mexico 87545

ELECTRON MICROSCOPY OF ALPHA-PLUTONIUM

K. P. Staudhammer, K. A. Johnson, M. Stevens and W. J. Medina

Materials Science and Technology Division
Los Alamos National Laboratory
Los Alamos, NM 87545

During the past several decades metallurgists world-wide have sought for a reliable and reasonable method to characterize plutonium and its alloys via transmission electron microscopy. Metallurgically, plutonium (Pu) represents one of the most fascinating metals; it has six solid phases and contracts when melted.

x x

A number of workers over the years have tried to produce thin foils of plutonium, but the foils were later shown to have been completely converted to oxide.^{1,2} The primary problem has been in the preparation of electron transparent thin foils of a material having one of the highest atomic numbers that is highly oxidation prone, in addition to being radioactive. Advances in Pu metallography in the late 70's and early 80's produced a new series of electro-chemical thinning solutions modified for plutonium.³⁻⁵ The δ (FCC) phase was first prepared using the techniques employed for this work and has been reported previously.⁶ This investigation has focused on the higher density, lower symmetry structure (monoclinic) α phase and is part of a larger study on plutonium and its alloys, and is the first reported TEM success with the alpha phase of Pu. Optical microscopy of the alpha phase has been very frustrating for years with many workers in the field speculating on the nature of the transformation to alpha from the higher temperature phases. Support for these theories has been delayed pending confirmation by TEM. The alpha crystal structure determined by Zachariasen and Ellinger^{7,8} from x-ray powder patterns in 1957 has not been confirmed by any single crystal diffraction work, to date. We have obtained for the first time TEM and SAD of the individual α phase crystallites of Pu. These are shown in Figs. 1 and 2. Computer aided electron diffraction analysis⁹ identified the SAD of Fig. 2 to be [010] and is shown in Fig. 3. Comparisons with the calculated pattern clearly substantiates the Zachariasen-Ellinger monoclinic structure and lattice parameter to within the accuracy of the TEM technique. All the TEM samples observed have traces of PuO₂ (FCC) on the surfaces. This is evident in Fig. 4 showing both the [001] α -Pu and the FCC PuO₂. These oxide layers appear to grow with a preferred or epitaxial orientation.

x


The preparation, environment, thinning solutions and transfer mechanisms used in this investigation are reported elsewhere.⁶

References

1. A. W. Brewer and F. J. Fraikor, J. Nucl. Mater. 21, 345-348 (1967).
2. R. Busch, "Transmission Electron Microscopy of Plutonium", Pacific Northwest Laboratory report BNWL-1863 (1974).
3. K. A. Johnson, "The Alternating Current Electroetching of Plutonium", Los Alamos Scientific Laboratory report LA-3173-MS 10/64.
4. K. A. Johnson, "Metallography", in Plutonium Handbook, O.J. Wick ed. (Gordon Breach, New York, Vol. 1, Chap. 9 (1967).
5. F. M. Cramer and J. B. Bergin "Plutonium Microstructures" Lawrence Livermore National Laboratory UCRL-53174, Dec. (1983).
6. D. L. Rohr, K. P. Staudhammer and K. A. Johnson, Los Alamos National Laboratory report LA-9965-MS March (1984).

K. P. Staudhammer

7. W. H. Zachariasen and F. Ellinger, Crystal Structure of Alpha-Plutonium Metal, J. Chem. Phys., 27:811 (1957).
8. W. H. Zachariasen and F. Ellinger, The Crystal Structure of Alpha Plutonium Metal, Acta Crystal, 16:777 (1963).
9. K. A. Johnson and L. McGaveran, PC-XTAL, An Electron Diffraction Analysis Program, Los Alamos National Laboratory (in preparation).



3

Fig 1.--Grain boundaries in α -Pu. Bar = 0.25 μ m.
 Fig 2.--SAD of α -Pu, (020).
 Fig 3.--Calculated diffraction pattern (020).
 Fig 4.--SAD of α -Pu (001) showing PuO_2 oxide trace.