

LA-8567-MS

C.I



Melting Under Shock Compression

University of California



3 9338 00311 0771

For Reference

Not to be taken from this room



LOS ALAMOS SCIENTIFIC LABORATORY

Post Office Box 1663 Los Alamos, New Mexico 87545

An Affirmative Action/Equal Opportunity Employer

This report was not edited by the Technical Information staff.

This work was supported by the US Department of Energy, Office of Basic Energy Sciences.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

**UNITED STATES
DEPARTMENT OF ENERGY
CONTRACT W-7405-ENG. 36**

LA-8567-MS

UC-34

Issued: October 1980

Melting Under Shock Compression

B. I. Bennett



LOS ALAMOS NATIONAL LABORATORY



3 9338 00311 0771



MELTING UNDER SHOCK COMPRESSION

by

B. I. Bennett

ABSTRACT

A simple model, using experimentally measured shock and particle velocities, is applied to the Lindemann melting formula to predict the density, temperature, and pressure at which a material will melt when shocked from room temperature and zero pressure initial conditions.

The formula for melting of a solid¹ obtained by Lindemann assumed that the material would melt when the r.m.s. atomic displacement of an atom in the lattice reached 1/8 of the nearest neighbor distance. This model produced the following formula for the melting temperature.

$$T_M = \left[\frac{\theta A^{5/6}}{B \rho^{1/3}} \right]^2, \quad (1)$$

where θ is the Debye temperature, A is the atomic weight, ρ is the material density, and B is a constant which varies from material to material. This constant B ranges over values of approximately 120 to 230 for a wide selection of elements. For purposes of this study, the value of B will be assumed independent of material density. In particular, it will be assumed that the melting formula will have a dependence dictated by the explicit density term appearing in the formula and the implicit dependence of the Debye temperature upon density. With these assumptions in mind, we may write an expression for the melting temperature of a material under compression.

$$T_M(\rho) = T_M(\rho_R) \left[\frac{\theta(\rho)}{\theta(\rho_R)} \frac{\rho_R^{1/3}}{\rho^{1/3}} \right]^2, \quad (2)$$

where $T_M(\rho_R)$ is the melting temperature at some reference density, ρ_R , say for conditions of zero pressure and room temperature. Written in this manner we need only concern ourselves with the variation of θ with compression and use an experimentally determined value for $T_M(\rho_R)$.

A convenient expression for the Debye temperature which encompasses three commonly used forms is given by²:

$$\theta(\rho) = K \rho^{\frac{t-2}{3}} \left[\rho^2 \frac{d}{d\rho} \left(\rho^{-\frac{2t}{3}} P_c \right) \right]^{\frac{1}{2}}, \quad (3)$$

where K is a constant. The parameter t yields the following choices for θ .

$$t = \begin{cases} 0, & \text{Slater-Landau expression}^{3,4} \\ 1, & \text{Dugdale-MacDonald expression}^5 \\ 2, & \text{"free-volume" expression}^6 \end{cases} .$$

The quantity, P_c , is the pressure obtained from the binding energy expression at $T = 0$. This equation for θ produces a Grüneisen parameter, from the definition

$$\Gamma(\rho) = \frac{\rho}{\theta(\rho)} \frac{d}{d\rho} \theta(\rho), \quad (4)$$

which asymptotes to a value of $2/3$ (free electron gas) at large compressions and at normal solid densities gives the following relationship between the choices of the parameter t for the given P_c .

$$\Gamma_{S-L} = \Gamma_{D-M} + \frac{1}{3} = \Gamma_{f-v} + \frac{2}{3}. \quad (5)$$

For metals, it has been observed with some reservation⁷ that the Dugdale-MacDonald formula (t=1) is useful for the analysis of shock data.

From Eq. (3) we find that

$$\left[\frac{\theta(\rho)}{\theta(\rho_R)} \right]^2 = \left(\frac{\rho_R}{\rho} \right)^{1/3} \frac{\left[\frac{dP_c}{d\rho} - \frac{2t}{3} P_c \right]}{\left[\frac{dP_c}{d\rho} - \frac{2t}{3} P_c \right]_{\rho_R}}, \quad (6)$$

allowing us, by way of Eq. (2), to express the Lindemann melting formula in terms of the density and the cold compression curve (i.e., pressure along the T=0 isotherm).

$$T_M(\rho) = T_M(\rho_R) \frac{\rho_R}{\rho} \frac{\left[\frac{dP_c}{d\rho} - \frac{2t}{3} P_c \right]}{\left[\frac{dP_c}{d\rho} - \frac{2t}{3} P_c \right]_{\rho_R}}. \quad (7)$$

This enables us to predict the melting temperature at any compression provided that: a) The Lindemann melting formula is valid; b) The Al'tshuler expression, Eq. (3), is appropriate for Debye temperatures at compressed densities; c) We have the value of the zero temperature pressure and its derivative at the compressed density.

This latter point of knowing the cold compression curve and its derivative has been addressed in Ref. 7. If it is assumed that the finite temperature contribution to the pressure obeys a Mie-Grüneisen form,

$$P - P_c = \rho \Gamma(\rho) [E - E_c], \quad (8)$$

then applying the energy and mass conservation conditions for a shocked material (i.e., the Hugoniot relations)⁷ the following equation is obtained.

$$P_H(\rho) = \frac{P_c(\rho) + \Gamma(\rho) P(\rho_R) \left[\frac{\rho - \rho_R}{2\rho_R} \right] - \Gamma(\rho) \rho \left[E_c(\rho) - E(\rho_R) \right]}{1 - \Gamma(\rho) \left[\frac{\rho - \rho_R}{2\rho_R} \right]} \quad (9)$$

Here $P(\rho_R)$ and $E(\rho_R)$ are the pressure and energy of the initial state before it is shocked to a pressure P_H and density ρ . Recalling that $\theta(\rho)$ and hence $\Gamma(\rho)$ can be expressed as a functional of P_c and its derivatives, we obtain a differential equation for the cold curve in terms of the shock pressure. Moreover, from the Hugoniot relations, we have

$$P_H = \rho_R U_S U_p \quad , \quad (10a)$$

and

$$\rho/\rho_R = U_S/(U_S - U_p) \quad , \quad (10b)$$

where U_S and U_p are the shock and particle speeds in the material.

In practice, it is observed that U_S and U_p for many materials are related by a linear expression.

$$U_S \cong C_0 + S U_p \quad . \quad (11)$$

Therefore, using the experimentally determined values of C_0 and S ,⁸ we may obtain $P_c(\rho)$ and $E_c(\rho)$.

We are now in a position to evaluate Eq. (7) to predict a melting temperature as a function of density. To determine if a material melts under shocked compression, we must be able to compute the temperature of the material along the Hugoniot curve.

To obtain the temperature dependence of the pressure and energy we use, for the thermal contribution, the Debye model. This choice is consistent with the assumption of a Mie-Grüneisen form.

$$E_{\theta}(\rho, T) = 3N_o kT \left[D(X_D) + \frac{3}{8} X_D \right] \quad (12a)$$

$$P_{\theta}(\rho, T) = \rho \Gamma(\rho) E_{\theta}(\rho, T) \quad , \quad (12b)$$

where $X_D \equiv \theta(\rho)/T$, N_o is the number of atoms per gram of material, and $D(X)$ is the Debye integral. The total internal energy and pressure are then given by:

$$E(\rho, T) = E_c(\rho) + E_{\theta}(\rho, T) \quad , \quad (13a)$$

$$P(\rho, T) = P_c(\rho) + P_{\theta}(\rho, T) \quad . \quad (13b)$$

By applying the Hugoniot relations with this simple equation of state, we are able to compute the temperature along the shock pressure curve to determine the density, temperature and pressure at which the Lindemann melting law would predict the material to melt. The results for a variety of materials are presented in Table I. Also included in the table are the shock and particle velocities at this point and the predicted compression, $\eta_M \equiv \rho/\rho_R$, of the initial density.

The table entries were obtained using the Dugdale-MacDonald form of the Debye temperature. The Slater-Landau and "free-volume" expressions raise and lower respectively the predicted pressure at which the material melts. An additional piece of experimental data such as the bulk modulus or the Grüneisen constant could be used to determine the appropriate value of t . In fact, it could be treated as an empirical parameter with nonintegral values and correspondingly adjusted to fit such data.

It would not be unexpected that factors such as whether or not the material underwent inelastic flow or the geometry of the shock compression could influence the outcome of experimental studies. However, if techniques could be devised to detect melting, this model might provide a test of the validity of the Lindemann formula.

TABLE I
RESULTS FOR A VARIETY OF MATERIALS

Material	ρ (gm/cc) <u>M</u>	T (°K) <u>M</u>	P (Mbars) <u>M</u>	U (km/S) <u>S</u>	U (km/S) <u>p</u>	η <u>M</u>
Al	4.065	2178	0.743	9.204	2.897	1.459
Au	26.455	3652	1.501	5.349	1.459	1.375
Be	3.113	3139	1.615	14.672	5.948	1.682
Bi	13.243	1257	0.219	2.940	0.756	1.346
Ca	2.532	1600	0.196	5.707	2.220	1.637
Cd	11.784	1816	0.450	4.419	1.179	1.364
Cr	10.922	6864	2.766	10.562	3.680	1.535
Cu	13.271	4087	1.721	7.676	2.511	1.486
Mo	15.368	6095	2.613	8.730	2.933	1.506
Na	1.407	730	0.055	4.250	1.326	1.453
Ni	13.327	4938	2.318	8.842	2.955	1.502
Pb	15.185	1345	0.302	3.248	0.820	1.338
Sb	10.146	3696	0.463	4.511	1.532	1.514
Ti	7.293	2022	0.930	7.361	2.791	1.611
W	29.873	8125	3.492	7.138	2.545	1.554

REFERENCES

1. J. M. Ziman, Electrons and Phonons, Oxford University Press, London (1963), p. 57.
2. L. V. Al'tshuler, Soviet Physics 8, 52 (1965).
3. J. C. Slater, Introduction to Chemical Physics, McGraw-Hill, New York (1939), Chapter XIV.
4. L. D. Landau and K. P. Stanyukovich, DAN SSSR 46, 399 (1945).
5. J. S. Dugdale and D. K. C. MacDonald, Phys. Rev. 89, 832 (1953).
6. Hirschfelder, Curtiss and Bird, Molecular Theory of Gases and Liquids, Wiley, New York (1954).
7. M. H. Rice, R. G. McQueen, and J. M. Walsh, "Compression of Solids by Strong Shock Waves," Solid State Physics, Academic Press, New York (1958), Vol. 6, p. 1.
8. "Selected Hugoniot," Los alamos Scientific Laboratory report LA-4167-MS (1969).

Printed in the United States of America
 Available from
 National Technical Information Service
 US Department of Commerce
 5285 Port Royal Road
 Springfield, VA 22161
 Microfiche \$3.50 (A01)

Page Range	Domestic Price	NTIS Price Code	Page Range	Domestic Price	NTIS Price Code	Page Range	Domestic Price	NTIS Price Code	Page Range	Domestic Price	NTIS Price Code
001-025	\$ 5.00	A02	151-175	\$11.00	A08	301-325	\$17.00	A14	451-475	\$23.00	A20
026-050	6.00	A03	176-200	12.00	A09	326-350	18.00	A15	476-500	24.00	A21
051-075	7.00	A04	201-225	13.00	A10	351-375	19.00	A16	501-525	25.00	A22
076-100	8.00	A05	226-250	14.00	A11	376-400	20.00	A17	526-550	26.00	A23
101-125	9.00	A06	251-275	15.00	A12	401-425	21.00	A18	551-575	27.00	A24
126-150	10.00	A07	276-300	16.00	A13	426-450	22.00	A19	576-600	28.00	A25
									601-up	†	A99

†Add \$1.00 for each additional 25-page increment or portion thereof from 601 pages up.

REPORT LAST
RECEIVED
OCT 24 1980
LIBRARY