


CIC-14 REPORT COLLECTION
**REPRODUCTION
COPY**



UNCLASSIFIED

LA-2336

Copy No. **0.3**A

AEC RESEARCH AND DEVELOPMENT REPORT

**LOS ALAMOS SCIENTIFIC LABORATORY
OF THE UNIVERSITY OF CALIFORNIA • LOS ALAMOS NEW MEXICO**

THE HEAT OF COMBUSTION OF δ -PLUTONIUM
(Title unclassified)



UNCLASSIFIED

UNCLASSIFIED

03175

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:


A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

03175

UNCLASSIFIED



LA-2336
C-16-CHEMISTRY-TRANSURANIC ELEMENTS
M-3679(23rd Ed.)

This document consists of 8 pages



LOS ALAMOS SCIENTIFIC LABORATORY
OF THE UNIVERSITY OF CALIFORNIA LOS ALAMOS NEW MEXICO

REPORT WRITTEN: July 1959

REPORT DISTRIBUTED: October 26, 1959

Classification changed to UNCLASSIFIED
by authority of the U. S. Atomic Energy Commission,

Per U.D.R. TID-1381 Suppl. 12-31-71

By REPORT LIBRARY Pete Martinez, 8-2-72

THE HEAT OF COMBUSTION OF δ -PLUTONIUM

(Title unclassified)

PUBLICLY RELEASABLE

Per Mark M. Jones, 10/27/95 FSS-16 Date: 10/27/95

By R. Collins, 11/8/95 CIC-14 Date: 11/8/95

by


Elmer J. Huber, Jr.
Earl L. Head
Charles E. Holley, Jr.

VERIFIED UNCLASSIFIED


Per Mark M. Jones 10/27/95

By R. Collins 11/8/95


Contract W-7405-ENG. 36 with the U. S. Atomic Energy Commission



LOS ALAMOS NATL. LAB. LIBS.
3 9338 00407 4620




UNCLASSIFIED



C-16, CHEMISTRY-TRANSURANIC ELEMENTS
 M-3679(23rd Ed.)
 LA-2336

Los Alamos Report Library	1-20
Aerojet-General, San Ramon (IOO-880)	21
Albuquerque Operations Office	22-23
Alco Products, Inc.	24
Argonne National Laboratory	25-26
Army Chemical Center	27
Atomic Energy Commission, Washington	28-30
Atomics International	31-32
Babcock and Wilcox Company (NYOO-1940)	33
Babcock and Wilcox Company (NYOO-274)	34
Bettis Plant (WAPD)	35-36
Brookhaven National Laboratory	37
BAR, Aerojet-General Azusa	38
Chicago Operations Office	39
Chicago Patent Group	40
Combustion Engineering, Inc.	41
duPont Company, Aiken	42-45
General Electric Company (ANPD)	46
General Electric Company, Richland	47-50
Goodyear Atomic Corporation	51
Hanford Operations Office	52
Iowa State College	53
Jet Propulsion Laboratory	54
Knolls Atomic Power Laboratory	55
Mallinckrodt Chemical Works	56
Marquardt Aircraft Company	57
Martin Company	58
Mound Laboratory	59
National Aeronautics and Space Administration, Cleveland	60
National Lead Company of Ohio	61
Naval Research Laboratory	62
New York Operations Office	63
Nuclear Metals, Inc.	64
Oak Ridge Operations Office	65
Patent Branch, Washington	66
Phillips Petroleum Company (NRTS)	67-68
Power Reactor Development Company	69
Union Carbide Nuclear Company (ORGDP)	70-71
Union Carbide Nuclear Company (ORNL)	72-75
USAF Project RAND	76
U.S. Naval Radiological Defense Laboratory	77
University of California at Los Angeles	78
University of California, Berkeley	79-80
University of California, Livermore	81-82
University of Rochester	83
Walter Reed Army Medical Center	84
Technical Information Service Extension	85-124



UNCLASSIFIED

CONFIDENTIAL

ABSTRACT

Precise measurements have been made of the heat of combustion of δ -plutonium metal. The heat of combustion of 1.01% gallium-stabilized δ -plutonium alloy was 4513.0 ± 7.2 joules/g at an oxygen pressure of 25 atm.

ACKNOWLEDGMENTS

The authors wish to express their appreciation for the advice and encouragement given by J. F. Lemons, Group Leader of CMF-2.

Valuable assistance was rendered by Group CMB-11 in the preparation of the plutonium metal, J. E. Mattys in the fabrication of the PuO_2 discs, and F. H. Ellinger in the X-ray analysis.

CONFIDENTIAL

~~CONFIDENTIAL~~
SECRET

CONTENTS

	Page
Abstract	3
Acknowledgments	3
Introduction	5
Method	5
δ -Plutonium Metal	5
Combustion of δ -Plutonium	6
Correction for Impurities	7
Bibliography	8

TABLE

I. The Heat of Combustion of δ -Plutonium	6
--	---

~~CONFIDENTIAL~~
SECRET

TOP SECRET

UNCLASSIFIED

Introduction

This report describes the measurements made with an oxygen combustion calorimeter, described earlier,¹ to determine the heat of combustion of gallium-stabilized δ -plutonium metal.

Method

The procedures used to handle the δ -plutonium metal and combustion products were identical to those employed for the combustion of α -plutonium metal.² The energy equivalent of the calorimeter with 25 atm. oxygen was $10,017.8 \pm 4.2$ joules/ $^{\circ}$ C. as determined with NBS benzoic acid. All runs were made at an oxygen pressure of 25 atm.


δ -Plutonium Metal

The δ -plutonium metal was analyzed at this Laboratory with the following results: Mg, 0.003%; Al, 0.01%; Si, 0.011%; Fe, 0.027%; Ca, 0.005%; Ni, 0.009%; Ga, 1.01%; C, 0.0115%; H, 0.000%; and O, 0.0015%. The metal was thus about 98.91% plutonium. If we assume that the carbon and oxygen were combined with the plutonium and not with the metallic impurities, the material was 96.01 mole % δ -plutonium metal.

-5-

TOP SECRET

UNCLASSIFIED




Combustion of δ -Plutonium


The combustions were performed on sintered discs of plutonium dioxide as described earlier.² Seven runs were made. Combustion was complete in each run except one in which 98.82% of the metal burned. X-ray patterns of the combustion products showed the lattice constant of the cubic unit cell, CaF₂ type, to be $a = 5.3949 \pm 0.0003 \text{ \AA}$. The average initial temperature was 25.3°C. The results are listed in Table I.

The heat of combustion of the 10 mil diameter δ -plutonium fuse wire used to ignite the main mass of the alloy was not determined separately. Its weight was only about 3% of the total weight and its heat of combustion could not have been sufficiently different to introduce a significant error.

Table I
THE HEAT OF COMBUSTION OF δ -PLUTONIUM

Mass δ -Pu Burned, g.	Wt. PuO ₂ , g.	joules/ ^o total	ΔT , °K.	Energy from		Dev. from Mean
				Firing, joules	Pu, joules/g.	
3.0109	124.6	10051.8	1.3527	8.1	4513.3	10.2
3.0668	122.3	10051.3	1.3814	8.6	4524.7	1.2
3.0071	121.6	10051.1	1.3547	6.8	4525.8	2.3
2.9777	117.8	10050.2	1.3393	6.7	4518.1	5.4
3.0402	116.5	10049.9	1.3701	6.5	4527.0	3.5
3.0251	129.8	10053.1	1.3655	5.4	4536.1	12.6
3.0243	124.2	10051.7	1.3604	5.1	4519.8	3.7
				Av.	4523.5	5.6
				2 x St. Dev.		5.6





 CONFIDENTIAL

The average value of 4523.5 joules/g. for the combustion of the alloy must be corrected for the impurities present.

Correction for Impurities

The calculated percentage composition of the δ -plutonium by weight is δ -Pu metal, 98.91%; Ga metal, 1.01%; PuO_2 , 0.013%; Mg, 0.003%; Al, 0.01%; Si, 0.011%; Ca, 0.005%; Ni, 0.009%; Fe, 0.027%; C, 0.0115%. The carbon may be combined with the plutonium as PuC but the amount is small. The heats of combustion of graphite (to CO_2), Mg (to MgO), Si (to SiO_2), Al (to Al_2O_3), Fe (to Fe_2O_3), Ca (to CaO), and Ni (to NiO_2) are taken as 33,000, 24,670, 30,100, 30,970, 7,320, 15,825, and 4,095 joules/g., respectively. The heat of combustion of the 1.01% gallium-stabilized δ -plutonium alloy, corrected for the presence of the impurities, becomes 4513.0 ± 7.2 joules/g., or 0.23% lower than the uncorrected value. If this value is now corrected for the presence of the gallium, taking 7710 joules/g. as its heat of combustion, the heat of combustion of δ -plutonium metal becomes 4480.3 joules/g. The heat of combustion of α -plutonium is 4413.4 ± 4.1 joules/g.² The difference between these two values may be attributed to (1) the heats of the α - β , β - γ , and γ - δ phase changes, (2) the heat of solution of gallium in plutonium, and (3) the heat of solution of Ga_2O_3 in PuO_2 (both X-ray and microscopic examination of the combustion product showed no separate Ga_2O_3 phase). Until additional data are obtained, perhaps from solution calorimetry, it will not be possible to calculate the heat of combustion of pure δ -plutonium metal.


7-

 CONFIDENTIAL

UNCLASSIFIED



Bibliography

- (1) Holley, C. E., Jr., and Huber, E. J., Jr., "A Precision Calorimeter for the Measurement of Heats of Combustion," LA-2084, November, 1955.
- (2) Huber, E. J., Jr., Head, E. L., and Holley, C. E., Jr., "The Heat of Combustion of Plutonium." LA-2279, November, 1958.



UNCLASSIFIED